

Co-Housing Trail

Typical crushed stone sieve analysis, based on crushed blue stone.

U.S. Sieve No.	Percent Passing by Weight
# 1/2"	95 – 100
# 3/8"	90 – 100
# 4	65 – 80
# 8	48 – 63
# 16	40 – 49
# 30	30 – 40
# 50	20 – 27
# 100	10 – 18
# 200	10 - 12